

# PRODUCT DATA SHEET

## GEOTEX® 104F

**GEOTEX 104F** is a woven monofilament polypropylene geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The individual filaments are woven into a regular network and calendared such that filaments retain dimensional stability relative to each other. These characteristics make **GEOTEX 104F** ideal for filtration beneath hard armor systems. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 104F** conforms to the property values listed below.<sup>1</sup> Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	MARV <sup>2</sup>	
		ENGLISH	METRIC
<b>Mechanical</b>			
Tensile Strength ( Grab )	ASTM D-4632	370 x 250 lbs	1,645 x 1110 N
Elongation	ASTM D-4632	24 x 24%	24 x 24%
Puncture	ASTM D-4833	120 lbs	535 N
Mullen Burst	ASTM D-3786	480 psi	3300 kPa
Trapezoidal Tear	ASTM D-4533	100 x 70 lbs	445 x 310 N
<b>Endurance</b>			
UV Resistance	ASTM D-4355	90%	90%
<b>Hydraulic</b>			
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	70 US Std. Sieve	0.212 mm
Percent Open Area (POA)	CW-02215 Mod. <sup>4</sup>	4%	4%
Permittivity	ASTM D-4491	0.28 sec <sup>-1</sup>	0.28 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	18 gpm/ft <sup>2</sup>	730 l/min/m <sup>2</sup>
<b>Roll Sizes</b>		6 ft x 300 ft 12 ft x 300 ft	1.83 m x 91.5 m 3.65 m x 91.5 m

#### NOTES:

1. The property values listed above are effective 08/2006 and are subject to change without notice.
2. Values for machine (warp) and cross-machine (fill), respectively, under dry or saturated conditions. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.
4. Army Corp of Engineers test method correlated to light emitted through fabric. (Area of Openings/Total Area X 100%)



THE ADVANTAGE CREATORS.™

Propex Inc.  
6025 Lee Highway, Suite 425  
PO Box 22788  
Chattanooga, TN 37422

PH: 423 899 0444  
PH: 800 621 1273  
FAX: 423 899 7619  
www.geotextile.com

Geotex®, Landlok®, Pyramat®, X3®, SuperGro®, Petromat® and Petrotac® are registered trademarks of Propex Inc. THIS PUBLICATION SHOULD NOT BE CONSTRUED AS ENGINEERING ADVICE. WHILE INFORMATION CONTAINED IN THIS PUBLICATION IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, PROPEX DOES NOT WARRANT ITS ACCURACY OR COMPLETENESS. THE ULTIMATE CUSTOMER AND USER OF THE PRODUCTS SHOULD ASSUME SOLE RESPONSIBILITY FOR THE FINAL DETERMINATION OF THE SUITABILITY OF THE INFORMATION AND THE PRODUCTS FOR THE CONTEMPLATED AND ACTUAL USE. THE ONLY WARRANTY MADE BY PROPEX FOR ITS PRODUCTS IS SET FORTH IN OUR PRODUCT DATA SHEETS FOR THE PRODUCT, OR SUCH OTHER WRITTEN WARRANTY AS MAY BE AGREED BY PROPEX AND INDIVIDUAL CUSTOMERS. PROPEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ARISING FROM PROVISION OF SAMPLES, A COURSE OF DEALING OR USAGE OF TRADE.