

PRODUCT DATA SHEET

GEOTEX® 106F

GEOTEX 106F is a woven monofilament polypropylene fabric produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The individual filaments are woven into a regular network and calendared such that filaments retain dimensional stability relative to each other. These characteristics make **GEOTEX 106F** ideal for filtration beneath hard armor systems. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX 106F conforms to the property values listed below.¹ Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	MARV ²	
		ENGLISH	METRIC
Mechanical			
Tensile Strength (Grab)	ASTM D-4632	300 x 200 lbs	1330 x 890 N
Elongation	ASTM D-4632	15 x 15%	15 x 15%
Puncture	ASTM D-4833	120 lbs	533 N
Mullen Burst	ASTM D-3786	450 psi	3100 kPa
Trapezoidal Tear	ASTM D-4533	65 x 65 lbs	285 x 285 N
Endurance			
UV Resistance	ASTM D-4355	90%	90%
Hydraulic			
Apparent Opening Size (AOS) ³	ASTM D-4751	40 US Std. Sieve	0.425 mm
Percent Open Area (POA)	CW-02215 Mod. ⁴	6%	6%
Permittivity	ASTM D-4491	0.5 sec ⁻¹	0.5 sec ⁻¹
Water Flow Rate	ASTM D-4491	35 gpm/ft ²	1420 l/min/m ²
Roll Sizes		12 ft x 330 ft	3.65 m x 100.6 m

NOTES:

1. The property values listed above are effective 08/2006 and are subject to change without notice.
2. Values for machine (warp) and cross-machine (fill), respectively, under dry or saturated conditions. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.
4. Army Corp of Engineers test method correlated to light emitted through fabric. (Area of Openings/Total Area X 100%)



THE ADVANTAGE CREATORS.™

Propex Inc.
6025 Lee Highway, Suite 425
PO Box 22788
Chattanooga, TN 37422

PH: 423 899 0444
PH: 800 621 1273
FAX: 423 899 7619
www.geotextile.com

Geotex®, Landlok®, Pyramat®, X3®, SuperGro®, Petromat® and Petrotac® are registered trademarks of Propex Inc.

THIS PUBLICATION SHOULD NOT BE CONSTRUED AS ENGINEERING ADVICE. WHILE INFORMATION CONTAINED IN THIS PUBLICATION IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, PROPEX DOES NOT WARRANT ITS ACCURACY OR COMPLETENESS. THE ULTIMATE CUSTOMER AND USER OF THE PRODUCTS SHOULD ASSUME SOLE RESPONSIBILITY FOR THE FINAL DETERMINATION OF THE SUITABILITY OF THE INFORMATION AND THE PRODUCTS FOR THE CONTEMPLATED AND ACTUAL USE. THE ONLY WARRANTY MADE BY PROPEX FOR ITS PRODUCTS IS SET FORTH IN OUR PRODUCT DATA SHEETS FOR THE PRODUCT, OR SUCH OTHER WRITTEN WARRANTY AS MAY BE AGREED BY PROPEX AND INDIVIDUAL CUSTOMERS. PROPEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ARISING FROM PROVISION OF SAMPLES, A COURSE OF DEALING OR USAGE OF TRADE.